



www.protectivepackaging.net

Certified: ISO 9001: 2015

PROTECT MP 12 (Medium Duty) JAN-B-121 G/C T/1 C/2 Data Sheet

Features: Greaseproof, waterproof, non-corrosive, moldable, and self-adhering. Resistant to delamination due to extreme weather conditions.

PHYSICAL PROPERTIES

MarvelPak 12 – Has wax on Both sides

Physical Property	Method	Test
Bursting Strength T403 (Mullen)	35 lbs / in ²	TAPPI
Tear Resistance T494 (MD & CD)	300 gms.	TAPPI
Tensile Strength T494 (MD / CD)	17/9 - # / in.	TAPPI
Adhesion to Aluminum Panel	18 lbs.	Mil-B-121F
Resistance to Heat & Humidity	No delamination	Exposed to 118 F 65% RH 5 Days

Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.