



www.protectivepackaging.net
 Certified: ISO 9001: 2008

PROTECT PPC VCI 40 Data Sheet

PRODUCT DESCRIPTION

40 Lb Poly coated Kraft; paper side saturated with a nitrite free chemical compound which provides protection of ferrous metals,

Typical Physical Test Results	Typical Values	TAPPI Test Method
Basis weight. Lbs/R (245x36-500)	59	T-410
Caliper, Mils	5.7	T-411
Tearing Strength, Elmendorf, gms. Machine Direction	24	T-414
Cross Machine Direction	13	
Bursting strength, PSI	37	T-403
Tensile Strength, (lbs/in.) Machine Direction	24	T-404
Cross Machine Direction	13	

Protect 40 PC W Ferro-Pak Metal Protection

Aluminum	Not Recommended
Steel, AISI 1010	Protection
Cast Iron	Testing Required
Brass, Red or White	Not Recommended
Bronze, including Naval	Testing Required
Copper	Not Recommended
Cadmium or Cadmium Plated	Not Recommended
Stainless Steel, All Grades	Protection
Galvanized, hot dipped or electroplated	Not Recommended
Chromium or Chromium Plated	Testing Required
Nickel or Nickel Plated	Testing Required
Silver or Silver Plated	Not Recommended
Magnesium	Not Recommended
Lead or solder	Not Recommended
Tin or tinplate	Protection
Zinc or White Metal	Not Recommended

Testing Required: this product will usually protect this metal type, however, for best results we recommend that testing be done. Protective Packaging always recommends corrosion testing of customer provided samples of metals and all chemicals to better confirm these statements

SHELF LIFE

This shelf life statement is only valid for product stored in the original shipping container and not in high humidity and not at high temperatures. Storage outside these conditions voids this statement.

Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.