



www.protectivepackaging.net

Certified: ISO 9001: 2008

PROTECT SCRIM-C MIL-PRF-131K Data Sheet

**Barrier Material: Watervaporproof, Greaseproof, Flexible, Heat-Sealable,
Class 3, Type 1 Structure description: PolyCotton-Scrim/PE/Foil/PE**

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUES	UNITS	TEST METHOD
Caliper	13.3	mil	ASTM D2103
Yield	3,270	in ² /lb	Calculated
Puncture Resistance	>22	lbs	MIL STD 3010
Tensile Strength	53	lbs	ASTM D882
OTR	0.0005	cc/100 in ² /day @0% RH, 23 °C	ASTM D3985
WVTR	0.0005	g/100 in ² /day @ 90% RH 40 °C	ASTM F1249
Seal Strength	10	lb/in	ASTM F88
Suggested Sealing Conditions	435 °F, 60psi, 3.0sec		

Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.