



www.protectivepackaging.net

Certified: ISO 9001: 2008

PROTECT STATIC SHIELDING Data Sheet

Static Shielding Material (SS) Buried Metal

Specifications: Anti-Static, Polyester, Metal Polyethylene, Anti-Static

Electrical Properties:	Typical Values	
Surface Resistivity/ Resistance Interior Exterior Metal	ASTM D257 <10 ¹² ohms/square <10 ¹² ohms/square 100 ohms	or ANSI/ESD STM11.11 or <10 ¹¹ ohms or <10 ¹¹ ohms
Static Shielding	<30 volts	MIL-PRF-81705, EIA 541
Static Shielding	<10 nJ	EOS/ESD S 11.31
Static Decay	<0.05 seconds	MIL-PRF-8/1705, FTMS1 101 MTH 4046
Charge Generation Teflon Quartz	0.09 nC/sq.in. 0.01 nC/sq.in.	Modified Inclined Plane
Physical Properties		
Tensile Strength	>25 lbs	ASTM D 882
Seam Strength	Pass	MIL-PRF-81705
Light Transmission	40%	Tobias
Heat Sealing Conditions Temperature Time Pressure	250 F – 375 F 0.5 – 3.5 seconds 30 – 70 PSI	
Thickness	3.1 mils	SCC 008
Outgassing	Pass	ASTM E595
Non-corrosive	Pass	FTMS MTH 3005

Disclaimer:

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

1746 West Crosby Road, Suite 108, Carrollton, Texas 75006
Ph: 972-446-2247 Fax: 972-446-2176